



USA  
 920 W. 10<sup>th</sup> St., Pella, IA 50219  
 1-855-527-4953

Canada  
 9-141 Reach St., Uxbridge, ON L9P 1L3  
 1-855-527-4953

**Ultem 9085 Material Properties**

Mechanical Properties	Test Method	Stratasys <sup>®</sup> Ultem 9085 Natural	Argyle Materials Ultem 9085 Natural
Tensile strength	ASTM D638	10762 psi	10762 psi
Tensile elongation	ASTM D638	6.08%	6.22%
Flexural strength	ASTM D790	12473 psi	13982 psi
Flexural modulus	ASTM D790	288625 psi	321984 psi
IZOD impact, notched	ASTM D256	2.30 ft-lb/in	1.79 ft-lb/in
IZOD impact, un-notched	ASTM D256	18.8 ft-lb/in	15.2 ft-lb/in
Thermal Properties			
Heat deflection @ 66psi	ASTM D648	340° F	340° F
Heat deflection @ 264psi	ASTM D648	324° F	328° F